

**SUPER-KRETE products and systems are warranted only when applied by persons Certified in writing by Super-Krete International, Inc. as Certified Super-Krete Applicators in accordance with manufacturer's guidelines on a structurally sound surface.**

## PRODUCT DESCRIPTION

SUPER-KRETE CLEAR SEAL PLUS is a water base acrylic/urethane copolymer emulsion, formulated for ease of application and maximum protection. The material penetrates the surface for a tenacious bond. SUPER-KRETE CLEAR SEAL PLUS provides a semi-gloss, uniform look over old and new surfaces, interior and exterior.

## SURFACE PREPARATION

*For detailed directions, see Super-Krete® Surface Preparation Application Specification S-1.*

1. Open any existing cracks using a diamond crack chasing blade.
2. Remove existing dirt, grime, laitance and debris mechanically using a blower. Shot-blasting, sand-blasting or acid washing/neutralizing should be performed to achieve a profiled surface. All surfaces to receive coatings must be profiled.
3. Clean and degrease the surface using Super-Krete Heavy Duty Degreaser™. *For detailed directions, see Super-Krete Product Specification S-12,000 Heavy Duty Degreaser.*
4. Prepare surface using Super-Krete Pene-Krete®. *For detailed directions, see Super-Krete Product Specification S-1300 Pene-Krete.*
5. Perform crack repair using the Super-Krete application Specification S-9900 Crack Repair.

## APPLICATION

Apply SUPER-KRETE CLEAR SEAL PLUS only with a filtered hand pump sprayer or airless sprayer. Set airless sprayer at lowest pressure setting and use nozzle of sufficient size to prevent atomization. Use a soft bristle broom to further spread material and provide uniformity. Do not roll. Do not allow product to puddle.

SUPER-KRETE CLEAR SEAL PLUS is to be used full strength. Do not dilute. Mix thoroughly with power mixer or manually prior to application.

1. Apply sealer in a light, even coat to lightly dampen surface only. Do not wet out surface and do not allow to puddle.
2. Follow immediately with a soft bristle broom to further spread material.
3. Allow first coat to fully dry (approx. one hour) and repeat application method until uniform. Two to three coats.

Note: Best results are achieved by one person spraying and another person following immediately with a broom or leaf blower.

## Limitations

SUPER-KRETE products are to be applied only when surface temperatures are above 55 degrees F and rising. SUPER-KRETE products are not to be applied when precipitation is expected within 24 hours following completion of application. Do not allow materials to freeze.

Note: SUPER-KRETE International, Inc. warrants this product to be of merchantable quality when used or applied by professional applicators approved by this company in strict accordance with manufacturer's specifications. SUPER-KRETE International, Inc. does not warrant this product for uses other than those intended. SUPER-KRETE International, Inc. does not make nor does it authorize any agent or representative to make any other warranty of MERCHANTABILITY OR FITNESS for purpose or any warranty, guarantee, or representation, express or implied, concerning this material except that it conforms to product specifications distributed by this company. SUPER-KRETE International, Inc. believes this information to be true to the best of our knowledge and products are of the highest quality and uniform within manufacturing tolerances. Since no control is exercised over product use, no warranty, expressed or implied, is made as to the effect of such use and no liability is assumed, directly or indirectly, from their use. Buyers and users accept this product under these conditions and assume the risk of any failure, injury, to person or property (including of buyer and user), death, loss or liability resulting from the handling, storage, or use of the product whether or not it is handled, stored, or used in accordance with directions or specifications. Any liability of this company to the buyer or user of this product is limited to the replacement value of the product. Buyers and users are encouraged to conduct their own test prior to application