

PENEPLUG

DESCRIPTION

Penepug is a rapid setting, integral crystalline cementitious waterstop designed to stop active water leaks and moisture ingress.

RECOMMENDED FOR

Penepug can be used internally or externally as a waterproof plugging mortar or where rapid setting and early strength gain is required.

- ◆ Plugging/stopping active water leaks
- ◆ Sealing of leaking joints, form tie holes or cracks

Penepug can be used on the following substrates:

- ◆ Concrete
- ◆ Masonry
- ◆ Earthenware
- ◆ Stone

ADVANTAGES

- ◆ Stops water flow
- ◆ Sets in approximately 30 seconds after mixing
- ◆ Durable
- ◆ Can be used underwater
- ◆ Can be mixed with water or used dry
- ◆ Easy to apply
- ◆ Packaged in easy to use, resealable containers

PACKAGING

This product can be purchased in 40 lb (18 kg) bags or 55 lb (25 kg) pails.

STORAGE

When stored in a dry place, in unopened, undamaged original packaging, shelf life is 12 months.

DIRECTIONS FOR USE

Surface Preparation:

The substrate must be clean, sound and free of any surface contamination. Leaks must be cut out back to sound material, leaving an appropriate chase for receiving the Penepug.

Mixing:

Setting time is dependent largely on the amount of mixing water used. Standard mix ratio at 68°F (20°C) is 2.5 lbs (1 kg) Penepug and approx. 1 cup (0.25 l) of water. The Penepug must be added to the water and mixed quickly. The mix should have a dry pack consistency. Mixing time is about 15 seconds with setting occurring about 30 seconds later. In cold weather, use lukewarm water. In higher temperatures, use cold water.

Application:

To avoid waste, only small quantities of Penepug should be mixed.

After mixing, apply the Penepug to the appropriate area immediately. Material should be formed into a wedge and forced into the leak. Work the mixture well into the area and then hold firmly in place for about 30 seconds. (Wear rubber gloves).

Maintain pressure without disturbing the material, until it has set. Apply as much pressure as possible, tapping in place with a block of wood and hammer if possible. After the leak has stopped, fill void to surface with Penecrete Mortar. Remove excess material.

After lightly pre-wetting apply a normal Penetron waterproofing coating. In certain circumstances Penepug may be applied as dry powder. Place and hold the powder directly over the leak for 30-60 seconds.

TECHNICAL DATA

Type	Powder
Color	Grey
Bulk Density	about 1.2 kg/l
Components	1 component
Application temperature	30°F to 77°F (-1°C to 25°C) (allow for mixing water and substrate temperatures)
Application time	about 30 seconds (after mixing)

HEALTH AND SAFETY

Penepug contains cement. Irritating to eyes and skin. May cause sensitization by skin contact. **KEEP OUT OF REACH OF CHILDREN.** Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Wear suitable gloves. For further information please refer to Material Safety Data Sheet.

WARRANTY

ICS PENETRON INTERNATIONAL LTD. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to ICS PENETRON INTERNATIONAL LTD. shall be limited to replacement of the material proven to be defective and shall in no case be liable otherwise or for incidental or consequential damages.

ICS PENETRON INTERNATIONAL LTD. MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED.

User shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith.