

SPECIFICATION DATA

1. Product Name

VERSI-TITE 12 oz. and 24 oz. cans

2. Manufacturer

RHH FOAM SYSTEMS, INC.
6001 South Pennsylvania Avenue
Cudahy WI 53110 USA
Telephone: 1-800-657-0702
 414-744-6066
FAX: 414-744-8227
E-Mail: sales@rhhfoamsystems.com
Web Site: www.rhhfoamsystems.com

3. Product Description

VERSI-TITE one component polyurethane foam sealant packaged in a 12 oz. can with straw applicator, 24 oz. can with straw applicator, and a 24 oz. can refill for use with dispensing gun.

4. Technical Data

VERSI-TITE 12 oz. and 24 oz. cans have the following physical properties:

DENSITY:	1.25 – 1.5 pounds per cubic foot	ASTM D1622
COMPRESSIVE STRENGTH:	7 psi (parallel)	ASTM D1621
TENSILE STRENGTH:	20 psi (parallel)	ASTM D1624
CLOSED CELL CONTENT:	=50%	ASTM D2856
FLAMESPREAD:	10	ASTM E84
SMOKE DEVELOPED:	20	ASTM E84
TACK FREE TIME:	Approx. 10 min. (70°F, 40%-60% Relative Humidity)	
CUTTABLE TIME:	Approx. 40 min.	
CURE TIME	Maximum 24 hours	
YIELD:	3/8" caulking bead	
	12 oz. can	950 linear feet
	24 oz. can (Straw Dispenser)	1920 linear feet
	24 oz. can (Refill for Gun)	1920 linear feet

Published yields are based on theoretical calculations and will vary depending on ambient conditions and the specific application. Physical properties shown are typical and are to serve only as a guide. Results are obtained from laboratory specimens under ideal laboratory conditions and may vary depending on the use, temperature and ambient conditions.